

### NORTHERN TERRITORY TO COMPLY MANUAL - National Construction Code Volume 2 (Section 3.0.4 Structural resistance of material in high wind areas) This product has been determined to satisfy NCC Performance Requirement P2.1.1 for structural stability and resistance.






LOCAL PRESSURE AREAS

A - general areas greater than  $\frac{a}{2}$  away from building corners (k<sub>L</sub> = 1.5)

C - up to  $\frac{a}{2}$  from building corners (k<sub>L</sub> = 2.0)

k<sub>1</sub> - local pressure zone factor applied to wind speed



**TYPICAL 6mm 'DURASHEET'** 

**FIXING DETAILS** 

WALL CLADDING REQUIREMENTS (REGION C)							
TERRAIN CATEGORY	LOCAL PRESSURE AREA	ULTIMATE LIMIT STATE PRESSURE (kPa)	STUD/BATTEN SPACING (mm)	FASTENER SPACING (mm)	TESTED CAPACITY PRESSURE (kPa)		
1	А	-3.10, +3.34	300	150	- 4.27		
	С	-4.13	300	150	- 4.27		
2	А	-2.33, +2.51	450	150	- 2.90		
2	С	-3.10	300	150	- 4.27		
2.5	А	-2.13, +2.29	450	200	- 2.19		
2.5	С	-2.84	450	150	- 2.90		
3 & 4	А	-1.94, +2.08	450	200	- 2.19		
584	C	-2.58	450	150	- 2.90		

#### CONSTRUCTION NOTES

'Durasheet' shall be fastened to a steel sub-frame in accordance with the support and fastener spacings tabulated above. Fasteners shall be fixed 12mm minimum from sheet edges and 50mm minimum from sheet corners.

All sheet edges and joints must be supported by steel framing.

Fasteners to steel supports from 0.75mm B.M.T. to 1.6mm B.M.T. shall be 'Buildex' or similar M5 Countersunk Ribbed Head self-drilling screws. Exposed 'Durasheet' cladding must be painted.

For fixing 'Durasheet' to built in mullions in steel stud walls up to 3.0mm thick use 'Buildex' WingTeks 10-16 CSK RIB

			Accepted for inclusion in Deemed to Comply Manual
			DTCM drawing number: M/261/01
Notes covering basis of DTC (Relevant Test reports etc) Tables are based on a test program to AS 4040.3:1992 clause 6, carried out by James Cook University Cyclone Testing Station in	Name: Adam James	Certifying Engineer Name: Peter Standen NT Registration Number: 289952ES	Chairperson Signature:
May 1997 (Test Report No TS486). We confirm AS 4040.3:1992 is equivalent to AS 4040.3:2018. The negative ULS pressures are deemed to govern, due to the	Date: 20/05/2021	N1 Registration Number: 209932E3         Date:       12/05/2021         Signiture:       Must be a registered structural engineer in the Northern Territory	Chairperson Name: Dr Elisha Harris
associated critical failure mechanism.	Signature: Must be an Australian registered structural engineer		Date of Approval: 3/04/2025 Expiry Date: 29/06/2026

### **Product Name**

## 6.0mm 'DURASHEET' Fibre Cement Cladding

# **Product Description**

# EXTERNAL WALL CLADDING

### Manufacturer's Details

etex Inspiring ways Etex Australia Pty Ltd - Innova Fibre Cement

21/31 Military Rd, Matraville NSW 2036

### Design Criteria

#### REGION 'C' WIND LOADING TO AS / NZS 1170.2:2011 (Including Amendment No 1, 2, 3, 4 & 5)

Limit State design pressures were determined in accordance with AS/NZS 1170.2:2011(including amendment No 1, 2, 3, 4 & 5) using shielding, topographic, combination, dynamic response, and structural importance multipliers equal to 1.0.

Strength: regional wind speed: V500 = 69m/s

Terrain/Height Multiplier (Mz cat):

### h ≤ 5m

TC

2.5

3&4

pressures

Limitations

1 2

1.05	Cpe = +0.7,-0.65
0.91	
0.87	
0.83	

1. These tables only apply to fixing to steel supports minimum thickness of steel support to be 0.75mm.

2. External cladding to be painted to manufacturers specifications.

3. Wall panels to be 2700 max height.

4. Domestic housing up to 5 meters high ( $h \le 5m$ ).

5. 6mm 'Durasheet' is an external cladding subject only to external pressure and suction loadings. Internal linings competent to resist

internal design pressures must be installed. The racking strength of Durasheet has not been tested and therefore should not be allowed for in the design of a structure.

6. The building aspect ratio (r) of the structure to be  $\leq 1$ . If r > 1 further checks of additional local pressures to be carried out by a fully qualified structural engineer. r is defined as the average roof height divided by the lesser of b and d.

7. A material capacity reduction factor of 0.8 was applied to the test capacity pressures nominated in the table to calculate the test

(Pt) used during the proof testing, which was carried out by Cyclone Structural Testing Station (James Cook University).